

TECHNICAL LIBRARY

ADA 678365

AD

TECHNICAL REPORT ARLCB-TR-79026

A NUMERICAL APPROACH TO ELASTIC-PLASTIC PLANE-STRAIN PROBLEMS OF THICK-WALLED CYLINDERS

P. C. T. Chen

October, 1979



US ARMY ARMAMENT RESEARCH AND DEVELOPMENT COMMAND
LARGE CALIBER WEAPON SYSTEMS LABORATORY
BENÉT WEAPONS LABORATORY
WATERVLIET, N. Y. 12189

AMCMS No. 6111.01.91A0.0

DA Project No. 1L161101A91A

PRON No. 1A-9-2ZA01-Y

APPROVED FOR PUBLIC RELEASE; DISTRIBUTION UNLIMITED

DISCLAIMER

The findings in this report are not to be construed as an official Department of the Army position unless so designated by other authorized documents.

The use of trade name(s) and/or manufacturer(s) does not constitute an official indorsement or approval.

DISPOSITION

Destroy this report when it is no longer needed. Do not return it to the originator.

REPORT DOCUMENTATION PAGE		READ INSTRUCTIONS BEFORE COMPLETING FORM
1. REPORT NUMBER ARLCB-TR-79026	2. GOVT ACCESSION NO.	3. RECIPIENT'S CATALOG NUMBER
4. TITLE (and Subtitle) A NUMERICAL APPROACH TO ELASTIC-PLASTIC PLANE-STRAIN PROBLEMS OF THICK-WALLED CYLINDERS		5. TYPE OF REPORT & PERIOD COVERED
		6. PERFORMING ORG. REPORT NUMBER
7. AUTHOR(s) P. C. T. Chen		8. CONTRACT OR GRANT NUMBER(s)
9. PERFORMING ORGANIZATION NAME AND ADDRESS Benet Weapons Laboratory Watervliet Arsenal, Watervliet, NY 12189 DRDAR-LCB-TL		10. PROGRAM ELEMENT, PROJECT, TASK AREA & WORK UNIT NUMBERS AMCMS No. 6111.01.91A0.0 DA Project No. 1L161101A91A PRON No. 1A-9-2Za01-Y
11. CONTROLLING OFFICE NAME AND ADDRESS US Army Armament Research and Development Command Large Caliber Weapon Systems Laboratory Dover, New Jersey 07801		12. REPORT DATE October 1979
		13. NUMBER OF PAGES 17
14. MONITORING AGENCY NAME & ADDRESS (if different from Controlling Office)		15. SECURITY CLASS. (of this report) UNCLASSIFIED
		15a. DECLASSIFICATION/DOWNGRADING SCHEDULE
16. DISTRIBUTION STATEMENT (of this Report) Approved for public release; distribution unlimited.		
17. DISTRIBUTION STATEMENT (of the abstract entered in Block 20, if different from Report)		
18. SUPPLEMENTARY NOTES Presented at Tenth Southeastern Conf on Theoretical & Applied Mechanics, 17-18 Apr 80, Univ of Tennessee, Knoxville, Tennessee. To be published in an open literature journal.		
19. KEY WORDS (Continue on reverse side if necessary and identify by block number) Elastic-Plastic Deformation Finite-Difference Method Gun Tube		
20. ABSTRACT (Continue on reverse side if necessary and identify by block number) A new finite-difference approach has been developed for solving the elastic-plastic plane-strain problems of thick-walled cylinders subjected to internal or external pressure. The material is assumed to obey the von Mises' yield criterion, the Prandtl-Reuss flow theory and the isotropic hardening rule. The numerical scheme is stable for ideally-plastic as well as straining-hardening materials. The approach is simpler than others, and very accurate solutions can be obtained by reducing the grid sizes and load increments. The results		

Cont from Block 20

for the stresses and strains in all principal directions have been computed as functions of loading history.

TABLE OF CONTENTS

	<u>Page</u>
INTRODUCTION	1
BASIC EQUATIONS	2
FINITE-DIFFERENCE FORMULATION	4
NUMERICAL RESULTS	7
REFERENCES	9

ILLUSTRATIONS

1. Internal pressure p or external pressure q as functions of elastic-plastic boundary ρ in an ideally-plastic tube.	10
2. Bore radial and tangential strains as functions of internal pressure p ; (a) ideally-plastic tube, (b) strain-hardening tube, $H' = E/19$.	11
3. Distributions of radial, tangential and axial stress components in an ideally-plastic tube subjected to internal pressure.	12
4. Bore radial and tangential strains as functions of external pressure q ; (a) ideally-plastic tube, (b) strain-hardening tube, $H' = E/19$.	13
5. Distributions of radial, tangential and axial stress components in an ideally-plastic tube subjected to external pressure.	14

INTRODUCTION

Based on a detailed study reported in Reference 1, the best material model for gun tubes under high pressure operation is an elastic-plastic material which obeys the Mises' yield criterion and the Prandtl-Reuss incremental stress-strain relation. A literature survey indicates that no closed form solution exists even for the axisymmetric plane-strain problems. And, in such situations, one has to rely on numerical methods. Both the finite-difference method^{2,3} and the finite-element method⁴ have been used to solve the elastoplastic problems considered here. The finite-element method is more powerful and can be used to solve more general elastoplastic problems. Since the displacement function is assumed and the programming is complicated, the accuracy of the finite-element approach has to be verified. This is usually done by comparing more rigorous solutions to simpler problems. For the problem considered here, rigorous solutions based on the finite-difference method were obtained by Hodge and White² for ideally-plastic materials and by Chu³ for strain-hardening materials.

¹Davidson, T. E., and Kendall, D. P., "The Design of Pressure Vessels For Very High Pressure Operation," Watervliet Arsenal Report WVT-6917. Also in Mechanical Behavior of Materials Under Pressure (edited by Pugh, H. L. D.), Elsevier Co., 1970, Chapter 2.

²White, P. G. and White, G. N., "A Quantitative Comparison of Flow and Deformation Theories of Plasticity," J. Appl. Mech., Vol. 17, 1950, pp. 180-184.

³Chu, S. C., "A More Rational Approach to the Problem of an Elastoplastic Thick-Walled Cylinder," J. of the Franklin Institute, Vol. 294, 1972, pp. 57-65.

⁴Chen, P. C. T., "The Finite Element Analysis of Elastic-Plastic Thick-Walled Tubes," Proceedings of Army Symposium on Solid Mechanics, 1972, The Role of Mechanics in Design-Ballistic Problems, pp. 243-253.

In the present paper, a new finite-difference approach is developed for solving the axisymmetric plane strain problems subjected to internal or external pressure beyond the elastic limit. An incremental approach is used, and the numerical scheme is stable for ideally-plastic as well as strain-hardening materials. The approach is simpler than others, yet very accurate solutions can be obtained by reducing the grid sizes and load increments.

BASIC EQUATIONS

Assuming small strain and no body forces in the axisymmetric state of plane strain, the radial and tangential stresses, σ_r and σ_θ , must satisfy the equilibrium equation,

$$r(\partial\sigma_r/\partial r) = \sigma_\theta - \sigma_r ; \quad (1)$$

and the corresponding strains, ϵ_r and ϵ_θ , are given in terms of the radial displacement, u , by

$$\epsilon_r = \partial u / \partial r , \quad \epsilon_\theta = u / r . \quad (2)$$

It follows that the strains must satisfy the equation of compatibility

$$r(\partial\epsilon_\theta/\partial r) = \epsilon_r - \epsilon_\theta . \quad (3)$$

Whereas the differential equations (1), (2) and (3) hold throughout the tube regardless of the material properties, the constitution equations assume various forms according to the adopted form of yield function, hardening rule, total or incremental theory of plasticity. In the present paper, the material is assumed to be elastic-plastic, obeying the Mises' yield criterion, the Prandtl-Reuss flow theory and the isotropic hardening law. The complete stress-strain relations are:⁵

⁵Hill, R., Mathematical Theory of Plasticity, Oxford University Press, 1950.

$$d\epsilon_i' = d\sigma_i'/2G + (3/2)\sigma_i'd\sigma/(\sigma H') \quad (4)$$

$$d\sigma \geq 0 \quad \text{for } i = r, \theta, z$$

$$d\epsilon_m = E^{-1}(1-2\nu)d\sigma_m \quad (5)$$

where E, ν Young's modulus, Poisson's respectively,

$$2G = E/(1+\nu)$$

$$\begin{aligned} \epsilon_m &= (\epsilon_r + \epsilon_\theta + \epsilon_z)/3, \quad \epsilon_i' = \epsilon_i - \epsilon_m, \\ \sigma_m &= (\sigma_r + \sigma_\theta + \sigma_z)/3, \quad \sigma_i' = \sigma_i - \sigma_m, \end{aligned} \quad (6)$$

$$\sigma = (1/\sqrt{2})[(\sigma_r - \sigma_\theta)^2 + (\sigma_\theta - \sigma_z)^2 + (\sigma_z - \sigma_r)^2]^{1/2} \geq \sigma_0,$$

and σ_0 is the yield stress in simple tension or compression. For a strain hardening material, H' is the slope of the effective stress/plastic strain curve

$$\sigma = H(\int d\epsilon^p). \quad (7)$$

For an ideally-plastic material ($H'=0$), the quantity $(3/2)d\sigma/(\sigma H')$ is replaced by $d\lambda$, a positive factor of proportionality. When $\sigma < \sigma_0$ or $d\sigma < 0$, the state of stress is elastic and the second term in equation (4) disappears. Following Yamada et al,⁶ equations (4) and (5) can be rewritten in an incremental form

$$d\sigma_i = d_{ij}d\epsilon_j \quad \text{for } i, j = r, \theta, z$$

and

$$d_{ij}/2G = \nu/(1-2\nu) + \delta_{ij} - \sigma_i'\sigma_j'/S, \quad (8)$$

⁶Yamada, Y., Yoshimura, N., and Sakurni, T., "Plastic Stress-Strain Matrix and Its Application for the Solution of Elastic-Plastic Problems by the Finite Element Method," Int. J. Mech. Sci., Vol. 10, 1968, pp. 343-354.

where

$$S = \frac{2}{3} \left(1 + \frac{1}{3} H'/G \right) \sigma^2 , \quad (9)$$

and δ_{ij} is the Kronecker delta.

This form was used in the finite-element formulation for solving elastic-plastic thick-walled tube problems.⁴ In the following section, the incremental stress-strain matrix will be used in the finite difference formulation.

FINITE-DIFFERENCE FORMULATION

Consider a thick-walled cylinder of inner radius a and external radius b . The tube is subjected to inner pressure p and/or external pressure q . The elastic solution for this problem is well-known and the pressure p^* or q^* required to cause initial yielding can be determined by using the Mises' yield criterion. For pressure beyond the elastic limit, an incremental approach of the finite-difference formulation is used. The analysis starts with the applied pressure p or q and the loading path is divided into m increments with

$$\Delta p = (p - p^*)/m , \quad \Delta q = (q - q^*)/m . \quad (10)$$

The cross section of the tube is divided into n rings with

$$r_1 = a, r_2, \dots, r_k = \rho, \dots, r_{n+1} = b, \quad (11)$$

⁴Chen, P. C. T., "The Finite Element Analysis of Elastic-Plastic Thick-Walled Tubes," Proceedings of Army Symposium on Solid Mechanics, 1972, The Role of Mechanics in Design-Ballistic Problems, pp. 243-253.

where ρ is the radius of the elastic-plastic interface. At the beginning of each increment of loading, the distribution of displacements, strains and stresses are assumed to be known and we want to determine Δu , $\Delta \epsilon_r$, $\Delta \epsilon_\theta$, $\Delta \sigma_r$, $\Delta \sigma_\theta$, $\Delta \sigma_z$ at all grid points. Since the incremental stresses are related to the incremental strains by the incremental form (Eq. (8)) and $\Delta u = r \Delta \epsilon_\theta$, there exists only two unknowns at each station that have to be determined for each increment of loading. The unknown variables in the present formulation are $(\Delta \epsilon_\theta)_i$, $(\Delta \epsilon_r)_i$, for $i = 1, 2, \dots, n, n+1$.

The equation of equilibrium (1) and the equation of compatibility (3) are valid for both the elastic and the plastic regions of a thick-walled tube. The finite-difference forms of these two equations at $i = 1, \dots, n$ are given in Reference 3 by

$$\begin{aligned} (r_{i+1} - 2r_i)(\Delta \sigma_r)_i - (r_{i+1} - r_i)(\Delta \sigma_\theta)_i + r_i(\Delta \sigma_r)_{i+1} \\ = (r_{i+1} - r_i)(\sigma_\theta - \sigma_r)_i - r_i[(\sigma_r)_{i+1} - (\sigma_r)_i] \end{aligned} \quad (12)$$

for the equation of equilibrium, and

$$\begin{aligned} (r_{i+1} - 2r_i)(\Delta \epsilon_\theta)_i - (r_{i+1} - r_i)(\Delta \epsilon_r)_i + r_i(\Delta \epsilon_\theta)_{i+1} \\ = (r_{i+1} - r_i)(\epsilon_r - \epsilon_\theta)_i - r_i[(\epsilon_\theta)_{i+1} - (\epsilon_\theta)_i] \end{aligned} \quad (13)$$

for the equation of compatibility.

³Chu, S. C., "A More Rational Approach to the Problem of an Elasto-Plastic Thick-Walled Cylinder," J. of the Franklin Institute, Vol. 294, 1972, pp. 57-65.

With the aid of the incremental stress-strain relations (Eq. (8)), equation (12) can be rewritten as

$$\begin{aligned}
& [(r_{i+1}-2r_i)(d_{12})_i + (-r_{i+1}+r_i)(d_{22})_i](\Delta\epsilon_\theta)_i \\
& + [(r_{i+1}-2r_i)(d_{11})_i + (-r_{i+1}+r_i)(d_{21})_i](\Delta\epsilon_r)_i \\
& + r_i(d_{12})_{i+1}(\Delta\epsilon_\theta)_{i+1} + r_i(d_{11})_{i+1}(\Delta\epsilon_r)_{i+1} \\
& = (r_{i+1}-r_i)(\sigma_\theta-\sigma_r)_i - r_i[(\sigma_r)_{i+1} - (\sigma_r)_i] .
\end{aligned} \tag{14}$$

The boundary conditions for the problem are

$$\Delta\sigma_r(a,t) = -\Delta p \quad , \quad \Delta\sigma_r(b,t) = -\Delta q . \tag{15}$$

Using the incremental relations (Eq. (8)), we rewrite equation (15) as

$$(d_{12})_1(\Delta\epsilon_\theta)_1 + (d_{11})_1(\Delta\epsilon_r)_1 = -\Delta p , \tag{16}$$

and

$$(d_{12})_{n+1}(\Delta\epsilon_\theta)_{n+1} + (d_{11})_{n+1}(\Delta\epsilon_r)_{n+1} = -\Delta q . \tag{17}$$

Now we can form a system of $2(n+1)$ equations for solving $2(n+1)$ unknowns, $(\Delta\epsilon_\theta)_i$, $(\Delta\epsilon_r)_i$, for $i = 1, 2, \dots, n, n+1$. Equations (16) and (17) are taken as the first and last equations, respectively, and the other $2n$ equations are set up at $i = 1, 2, \dots, n$ using (13) and (14). The final system is an unsymmetric band matrix with the nonzero terms clustered about the main diagonal, two below and one above. The storage required is $8(n+1)$ words for this system and at least $35(n+1)$ words for the approach.³ In the computer program which was developed, the Gaussian elimination method was used to solve these equations. All calculations were carried out on IBM 360/Model 44 with double precision to reduce round-off errors.

³Chu, S. C., "A More Rational Approach to the Problem of an Elasto-Plastic Thick-Walled Cylinder," J. of the Franklin Institute, Vol. 294; 1972, pp. 57-65.

NUMERICAL RESULTS

The plane-strain problems of thick-walled cylinders subjected to internal pressure p or external pressure q beyond the elastic limit were solved. The elastic-perfectly-plastic as well as strain-hardening materials were considered. The numerical results were based on the following parameters: $b/a = 2$, $\nu = 0.3$, $H' = 0$ or $E/19$. Various values of m and n were used to test the convergence of the numerical results. The incremental loadings were applied until the fully plastic state was reached. The values for p or q corresponding to this final state were denoted by p^{**} or q^{**} . It was found that the results for these values converge by increasing m and/or n . For an ideally-plastic tube under internal pressure only, we have $(n, m, p^{**}/\sigma_0) = (20, 1277, 0.81341)$, $(50, 1000, 0.80455)$, $(100, 998, 0.80155)$, $(200, 920, 0.80029)$. Since the storage needed for this approach is only 22% of that in Reference 3, much larger n can be used to yield better results. Additional results shown in Figures 1 to 5 were based on $n = 100$ and $m = 900-1000$. Figure 1 shows the relation between internal pressure p , external pressure q and elastic-plastic boundary ρ in an elastic-perfectly-plastic tube. Figure 2 shows the bore radial and tangential strains as functions of internal pressure p in an

³Chu, S. C., "A More Rational Approach to the Problem of an Elasto-Plastic Thick-Walled Cylinder," J. of the Franklin Institute, Vol. 294, 1972, pp. 57-65.

ideally-plastic as well as a strain-hardening tube. Figure 3 shows the distributions of radial, tangential and axial stresses in an ideally-plastic tube subjected to internal pressure. The dotted curves correspond to initial yielding. The solid and broken curves correspond to the cases when half and all of the tube is plastic, respectively. For an ideally-plastic tube subjected to external pressure q , the results were presented graphically in Figures 1, 4, and 5.

REFERENCES

1. Davidson, T. E. and Kendall, D. P., "The Design of Pressure Vessels For Very High Pressure Operation," Watervliet Arsenal Report WVT-6917. Also in Mechanical Behavior of Materials Under Pressure (edited by Pugh, H. L. D.), Elsevier Co., 1970, Chapter 2.
2. Hodge, P. G. and White, G. N., "A Quantitative Comparison of Flow and Deformation Theories of Plasticity," J. Appl. Mech., Vol. 17, 1950, pp. 180-184.
3. Chu, S. C., "A More Rational Approach to the Problem of an Elasto-Plastic Thick-Walled Cylinder," J. of the Franklin Institute, Vol. 294, 1972, pp. 57-65.
4. Chen, P. C. T., "The Finite Element Analysis of Elastic-Plastic Thick-Walled Tubes," Proceedings of Army Symposium on Solid Mechanics, 1972, The Role of Mechanics in Design-Ballistic Problems, pp. 243-253.
5. Hill, R., Mathematical Theory of Plasticity, Oxford University Press, 1950.
6. Yamada, Y., Yoshimura, N., and Sakurni, T., "Plastic Stress-Strain Matrix and Its Application for the Solution of Elastic-Plastic Problems by the Finite Element Method," Int. J. Mech. Sci., Vol. 10, 1968, pp. 343-354.




Figure 1. Internal pressure p or external pressure q as functions of elastic-plastic boundary ρ in an ideally-plastic tube




Figure 2. Bore radial and tangential strains as functions of internal pressure p
 (a) ideally-plastic tube, (b) strain-hardening tube, $H' = E/19$




Figure 3. Distributions of radial, tangential and axial stress components in an ideally-plastic tube subjected to internal pressure ($\rho/a = 1.0$, 1.5 ——— , 2.0 - - -)




Figure 4. Bore radial and tangential strains as functions of external pressure q
 (a) ideally-plastic tube, (b) strain-hardening tube, $H' = E/19$




Figure 5. Distributions of radial, tangential and axial stress components in an ideally-plastic tube subjected to external pressure ($\rho/a = 1.0$, 1.5 —, 2.0 — —)

WATERVLIET ARSENAL INTERNAL DISTRIBUTION LIST

	NO. OF COPIES
COMMANDER	1
DIRECTOR, BENET WEAPONS LABORATORY	1
CHIEF, DEVELOPMENT ENGINEERING BRANCH	1
ATTN: DRDAR-LCB-DA	1
-DM	1
-DP	1
-DR	1
-DS	1
-DC	1
CHIEF, ENGINEERING SUPPORT BRANCH	1
CHIEF, RESEARCH BRANCH	2
ATTN: DRDAR-LCB-RA	1
-RC	1
-RM	1
-RP	1
TECHNICAL LIBRARY	5
TECHNICAL PUBLICATIONS & EDITING UNIT	2
DIRECTOR, OPERATIONS DIRECTORATE	1
DIRECTOR, PROCUREMENT DIRECTORATE	1
DIRECTOR, PRODUCT ASSURANCE DIRECTORATE	1

NOTE: PLEASE NOTIFY DIRECTOR, BENET WEAPONS LABORATORY, ATTN: DRDAR-LCB-TL, OF ANY REQUIRED CHANGES.

EXTERNAL DISTRIBUTION LIST (CONT)

	<u>NO. OF COPIES</u>		<u>NO. OF COPIES</u>
COMMANDER US ARMY RESEARCH OFFICE P.O. BOX 1211 RESEARCH TRIANGLE PARK, NC 27709	1	COMMANDER DEFENSE DOCU CEN ATTN: DDC-TCA CAMERON STATION ALEXANDRIA, VA 22314	12
COMMANDER US ARMY HARRY DIAMOND LAB ATTN: TECH LIB 2800 POWDER MILL ROAD ADELPHIA, MD 20783	1	METALS & CERAMICS INFO CEN BATTELLE COLUMBUS LAB 505 KING AVE COLUMBUS, OHIO 43201	1
DIRECTOR US ARMY INDUSTRIAL BASE ENG ACT ATTN: DRXPE-MT ROCK ISLAND, IL 61201	1	MPDC 13919 W. BAY SHORE DR. TRAVERSE CITY, MI 49684	1
CHIEF, MATERIALS BRANCH US ARMY R&S GROUP, EUR BOX 65, FPO N.Y. 09510	1	MATERIEL SYSTEMS ANALYSIS ACTV ATTN: DRXSY-MP ABERDEEN PROVING GROUND MARYLAND 21005	1
COMMANDER NAVAL SURFACE WEAPONS CEN ATTN: CHIEF, MAT SCIENCE DIV DAHLGREN, VA 22448	1		
DIRECTOR US NAVAL RESEARCH LAB ATTN: DIR, MECH DIV CODE 26-27 (DOC LIB) WASHINGTON, D.C. 20375	1 1		
NASA SCIENTIFIC & TECH INFO FAC P.O. BOX 8757, ATTN: ACQ BR BALTIMORE/WASHINGTON INTL AIRPORT MARYLAND 21240	1		

NOTE: PLEASE NOTIFY COMMANDER, ARRADCOM, ATTN: BENET WEAPONS LABORATORY, DRDAR-LCB-TL, WATERVLIET ARSENAL, WATERVLIET, N.Y. 12189, OF ANY REQUIRED CHANGES.

EXTERNAL DISTRIBUTION LIST

	<u>NO. OF COPIES</u>		<u>NO. OF COPIES</u>
ASST SEC OF THE ARMY RESEARCH & DEVELOPMENT ATTN: DEP FOR SCI & TECH THE PENTAGON WASHINGTON, D.C. 20315	1	COMMANDER US ARMY TANK-AUTMV R&D COMD ATTN: TECH LIB - DRDTA-UL MAT LAB - DRDTA-RK WARREN, MICHIGAN 48090	1 1
COMMANDER US ARMY MAT DEV & READ. COMD ATTN: DRCDE 5001 EISENHOWER AVE ALEXANDRIA, VA 22333	1	COMMANDER US MILITARY ACADEMY ATTN: CHMN, MECH ENGR DEPT WEST POINT, NY 10996	1
COMMANDER US ARMY ARRADCOM ATTN: DRDAR-TSS DRDAR-LCA (PLASTICS TECH EVAL CEN)	2 1	COMMANDER REDSTONE ARSENAL ATTN: DRSMI-RB DRSMI-RRS DRSMI-RSM ALABAMA 35809	2 1 1
DOVER, NJ 07801		COMMANDER ROCK ISLAND ARSENAL ATTN: SARRI-ENM (MAT SCI DIV) ROCK ISLAND, IL 61202	1
COMMANDER US ARMY ARRCOM ATTN: DRSAR-LEP-L ROCK ISLAND ARSENAL ROCK ISLAND, IL 61299	1	COMMANDER HQ, US ARMY AVN SCH ATTN: OFC OF THE LIBRARIAN FT RUCKER, ALABAMA 36362	1
DIRECTOR US ARMY BALLISTIC RESEARCH LABORATORY ATTN: DRDAR-TSB-S (STINFO) ABERDEEN PROVING GROUND, MD 21005	1	COMMANDER US ARMY FGN SCIENCE & TECH CEN ATTN: DRXST-SD 220 7TH STREET, N.E. CHARLOTTESVILLE, VA 22901	1
COMMANDER US ARMY ELECTRONICS COMD ATTN: TECH LIB FT MONMOUTH, NJ 07703	1	COMMANDER US ARMY MATERIALS & MECHANICS RESEARCH CENTER ATTN: TECH LIB -DRXMR-PL WATERTOWN, MASS 02172	2
COMMANDER US ARMY MOBILITY EQUIP R&D COMD ATTN: TECH LIB FT BELVOIR, VA 22060	1		

NOTE: PLEASE NOTIFY COMMANDER, ARRADCOM, ATTN: BENET WEAPONS LABORATORY, DRDAR-ICB-TL, WATERVLIET ARSENAL, WATERVLIET, N.Y. 12189, OF ANY REQUIRED CHANGES.